

Product : Polyflor SD
Resistance To Chemicals

Date : Aug. 2006
Page 1 of 3

Resistance to chemicals is tested over a 24 hour contact period at room temperature (ca.21°C), followed by rinsing with cold water. Polyflor Ltd believe this simulates the worst situation where spillages are not removed immediately and are only cleaned by normal maintenance.

U - Unstained A - Slight stain B - Moderate stain C - Heavy stain
 E - Appearance as above plus slight surface disturbance

Chemical	Shade											
	5010	5020	5030	5040	5050	5060	5070	5080	5100	5110	5120	5130
Acetic Acid Glacial	U	U	U	U	U	U	U	U	U	U	U	U
Acetic Acid 50% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Acetic Acid 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Boric Acid 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Citric Acid 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Hydrochloric Acid Concentrated	U	U	U	U	U	U	U	U	U	U	U	U
Hydrochloric Acid 50% Solution	U	A	U	U	U	U	U	U	A	U	U	U
Hydrochloric Acid 10% Solution	U	A	U	U	U	U	U	U	A	U	U	U
Lactic Acid Concentrated	U	U	U	U	U	U	U	U	U	U	U	U
Nitric Acid Concentrated	U	A	U	U	A	U	B	U	U	U	A	U
Nitric Acid 50% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Nitric Acid 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Oxalic Acid 10% Solution	U	A	U	U	U	U	U	U	U	U	U	U
Perchloric Acid 60% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Phosphoric Acid Concentrated	B	A	U	U	A	U	A	B	U	A	A	U
Phosphoric Acid 50% Solution	B	A	U	U	A	U	A	B	U	A	A	U
Pyrogalllic Acid	C	C	C	C	C	C	C	C	C	C	C	C
Sulphuric Acid Concentrated	U	U	U	U	U	U	C	U	U	U	U	U
Sulphuric Acid 50% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Sulphuric Acid 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Tannic Acid 10% Solution	U	U	U	U	U	U	U	U	U	A	U	U
Tartaric Acid 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Thioglycollic Acid Concentrated	U	A	U	A	U	A	A	U	A	U	U	A
Absolute Alcohol	U	U	U	U	U	U	U	U	U	U	U	U
Amidol 10% Solution	U	A	U	A	B	A	C	U	A	U	B	A
Ammonia Solution 88	U	U	U	U	U	U	U	U	U	U	U	U
Ammonium Alum 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Ammonium Bichromate 10% Soln	U	U	U	U	U	U	A	U	U	U	U	U
Ammonium Bromide 10% Solution	A	A	U	U	A	U	U	A	A	A	A	U
Ammonium Carbonate 10% Soln	U	U	U	U	U	U	U	U	U	U	U	U
Ammonium Chloride 10% Solution xxxx	U	U	U	U	U	U	U	U	U	U	U	U
Ammonium Sulphate	B	B	A	A	U	A	U	B	A	U	U	A
Ammonium Thiocyanate 10% Soln	U	U	U	U	U	U	U	U	U	U	U	U
Borax 10% Solution	U	U	U	U	U	U	A	U	U	U	U	U
Calcium Chloride 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Calgon 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Carbon Tetrachloride	U	U	U	U	U	U	U	U	U	U	U	U
Catechol 10% Solution	C	C	C	C	C	C	B	C	C	B	C	C
Chrome Alum 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Copper Sulphate 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U

Product : Polyflor SD
Resistance To Chemicals

Date : Aug. 2006
Page 2 of 3

U - Unstained A - Slight stain B - Moderate stain C - Heavy stain
 E - Appearance as above plus slight surface disturbance

Chemical	Shade											
	5010	5020	5030	5040	5050	5060	5070	5080	5100	5110	5120	5130
Ferric Ammonium Citrate 10%soln	U	U	U	U	U	U	U	U	U	U	U	U
Formaldehyde 50% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Glycerine	U	U	U	U	U	U	U	U	U	U	U	U
Glycine 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Hydrogen Peroxide 100	U	U	U	U	U	U	U	U	U	U	U	U
Hydroquinone 10% Solution	U	U	A	A	U	U	A	U	A	A	U	U
Hydroxylamine Hydrochloride 10% Soln	U	U	U	U	U	U	U	U	U	U	U	U
Iodine 5% In Potassium Iodide Soln	A	A	A	B	B	B	B	A	A	B	B	B
Iodine Alcoholic Solution	U	U	U	A	A	A	B	U	U	U	A	A
Iron Perchloride 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Iron Sulphate 10% Solution	U	U	U	U	U	U	A	U	U	U	U	U
Lead Acetate 10% Solution	U	U	A	U	A	U	U	U	U	A	A	U
Magnesium Sulphate 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Metol 10% Solution	C	C	C	C	C	C	C	C	C	C	C	C
Mercuric Chloride 10%Solution	U	U	U	U	U	U	A	U	U	U	U	U
Methylated Spirits 10%Solution	U	U	U	U	U	U	U	U	U	U	U	U
Paraformaldehyde 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Phenol 10% Solution	B	U	U	U	U	U	U	B	U	U	U	U
Potassium Bromide 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Potassium Carbonate 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Potassium Dichromate 10% Soln	U	U	A	U	U	U	U	U	U	U	U	U
Potassium Ferricyanide 10% Soln	U	U	U	U	U	U	U	U	U	U	U	U
Potassium Ferrocyanide 10% Soln	U	U	U	U	U	U	U	U	U	U	U	U
Potassium Hydroxide 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Potassium Iodide 10% Solution	A	U	A	A	A	U	U	A	A	A	A	U
Potassium Metabisulphite 10% Soln	U	U	U	U	U	U	U	U	U	U	U	U
Potassium Oxalate 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Potassium Permanganate 10% Soln	B	B	B	C	C	A	A	B	B	B	C	A
Potassium Thiocyanate 10% Soln	U	U	U	U	U	U	U	U	U	U	U	U
Silver Nitrate 10% Solution	C	C	B	C	C	B	A	C	C	C	C	B
Sodium Acetate 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Sodium Bicarbonate 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Sodium Bromide 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Sodium Carbonate 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Sodium Chloride 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Sodium Hydroxide 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Sodium Hypochlorite 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Sodium Perborate 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Sodium Phosphate 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Sodium Sulphate 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Sodium Sulphite 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U
Sodium Thiosulphate 10% Solution	U	U	U	U	U	U	U	U	U	U	U	U

Product : Polyflor SD
Resistance To Chemicals

Date : Aug. 2006
Page 3 of 3

U - Unstained A - Slight stain B - Moderate stain C - Heavy stain
 E - Appearance as above plus slight surface disturbance

Chemical	Shade											
	5010	5020	5030	5040	5050	5060	5070	5080	5100	5110	5120	5130
Izal Concentrated	B	A	A	B	A	A	A	B	A	A	A	A
Izal Diluted	U	U	U	U	U	U	U	U	U	U	U	U
TCP Concentrated	U	U	U	U	U	U	U	U	U	U	U	U
Dettol Concentrated	U	U	U	U	U	U	U	U	U	U	U	U
Soap Solutions	U	U	U	U	U	U	U	U	U	U	U	U
Detergent Solutions	U	U	U	U	U	U	U	U	U	U	U	U
Milk	U	U	U	U	U	U	U	U	U	U	U	U
Tea (black)	U	U	U	U	U	U	U	U	U	U	U	U
Coffee (black)	U	U	U	U	U	U	U	U	U	U	U	U
Petrol	U	U	U	U	U	U	U	U	U	U	U	U
White Spirit	U	U	U	U	U	U	U	U	U	U	U	U
Diesel Fuel	U	U	U	U	U	U	U	U	U	U	U	U
Mineral Oil (Singer)	U	U	U	U	U	U	U	U	U	U	U	U
Vegetable Oil	U	U	U	U	U	U	U	U	U	U	U	U
Anti Freeze (Bluecol)	U	U	U	A	U	U	U	U	U	U	U	U

