



- The flooring shall be Polyflor Sport, as supplied by Polyflor Ltd. of Manchester, England.
- The flooring shall be flexible PVC sheet flooring in 6.7mm thickness.
- The total thickness shall be made up of a surface wear layer, which shall be homogeneous and monolayer in construction; glassfibre reinforcement and closed cell foam layer.



- The flooring material shall have been tested in accordance with European Standards as given below.
- In respect of flamespread, the flooring shall have been fully tested to EN 13501-1 and certified as having Class Cf1-S1, achieving the criteria EN ISO 9239-1 >4.5kw/m<sup>2</sup> and the mandatory requirement of EN ISO 11925-2 pass.
- With regard to EN 13893 for slip resistance, the flooring shall be classified as DS, making it suitable for use in areas which are predominantly dry but with occasional spillages.
- The product must be classified abrasion group T, as defined in EN 660-2.
- This product does not accumulate static charges above 2kV and is classified as 'antistatic' when tested to EN 1815. For specialist applications where there is a requirement to dissipate the electrostatic charge, see the Polyflor ESD product ranges.
- The flooring must be available in 2.0 metre width, to minimise the number of joints.



- The manufacturer of the floorcovering must be in possession of a valid quality systems certificate, showing compliance with BS EN ISO 9001: 2000.
- The manufacturer of the floorcovering must be in possession of a valid environmental certificate, showing compliance with ISO 14001.



- A moisture test must be carried out, to ensure that the subfloor has dried out to a level consistent with the application of vinyl flooring. The test should be out using a hygrometer, in accordance with the instructions in BS 8203. The result should not exceed 75%RH, once equilibrium has been achieved.
- The adhesive used must be approved by Polyflor, to ensure full product compatibility.
- Products must be fully conditioned to the environment in which they are to be installed, as outlined by Polyflor.
- Installation must be carried out in accordance with BS 8203 and the instructions of Polyflor.
- All joints must be welded.



- Polyflor Sport is recommended for use in school and local authority sports halls, gymnasias and leisure centres where a degree of resilience underfoot and long life under heavy traffic are needed. For further information and advice on specific applications, consult Polyflor Customer Technical Support on +44 (0)161 767 1912, or email tech@polyflor.com.



- At the date of issue the data presented is correct. However, Polyflor Ltd. reserves the right to make changes which do not adversely affect performance or quality.

For line markings onto the Polyflor Sport 67 and 80, we would suggest using the following line marking contractors, who are all experienced and familiar with the practice of line marking the Polyflor range of floorcoverings.

**Sports Court/Line Marking Approved Contractors**

**Sportsmark Group Ltd**  
Sportsmark House, 4 Clerewater Place  
Lower Way, Thatcham RG19 3RF

Mike Pocklington  
Tel : 01635 867537

**Renovate Contracts**  
PO Box 6629, Earl Shilton  
Leicestershire LE9 7ZY

Duncan or Tom  
Tel/Fax: 01455 851900  
Mobile: 07773846587

**Francis Coatings**  
23 Chestnut Drive, Holmes Chapel  
Cheshire CW4 7QE

Brad Francis  
Tel/Fax: 01477 544149

All the above contractors carry out work in all locations across the UK.

POLYFLOR LTD. PO BOX 3 RADCLIFFE NEW ROAD WHITEFIELD MANCHESTER M45 7NR UK  
TEL: +44 (0)161 767 1111 UK SALES DIRECT: +44 (0)161 767 1122 UK FAX: +44 (0)161 767 1128  
EXPORT FAX: +44 (0)161 767 1166 E-MAIL: INFO@POLYFLOR.COM WWW.POLYFLOR.COM  
UK SAMPLE REQUESTS: +44 (0)161 767 2551



POLYFLOR  
**SPORT67**

PRODUCT SPECIFICATION