



















# CAMARO™

The Camaro range features a variety of different wood and stone textures designed to replicate the original material. These are both decorative and practical offering durability, sound reduction and the ability to install and maintain easily. Common use areas for Camaro include mainly residential or light commercial.

	<b>Gauge</b>	EN ISO 24346 (EN 428)	2.0mm (0.08")
	<b>Wear Layer</b>	EN ISO 24340 (EN 429)	0.3mm (0.012")
	<b>Plank Size</b>	EN ISO 24342 (EN 427)	192 @ 76.2 x 228.6mm = 3.34m <sup>2</sup> (3" x 9" = 35.95ft <sup>2</sup> ) 36 @ 101.6 x 914.4mm = 3.34m <sup>2</sup> (4" x 36" = 35.95ft <sup>2</sup> ) 24 @ 152.4 x 914.4mm = 3.34m <sup>2</sup> (6" x 36" = 35.95ft <sup>2</sup> ) 18 @ 152.4 x 1219.2mm = 3.34m <sup>2</sup> (6" x 48" = 35.95ft <sup>2</sup> ) 15 @ 184.2 x 1219.2mm = 3.37m <sup>2</sup> (7.25" x 48" = 36.27ft <sup>2</sup> ) 12 x 3 @ 76.2/101.6/152.4 x 914.4mm = 3.62m <sup>2</sup> (3"/4"/6" x 36" = 38.97ft <sup>2</sup> ) 14 @ 203.2 x 1219.2mm = 3.46m <sup>2</sup> (8" x 48" = 37.24ft <sup>2</sup> )
	<b>Tile Size</b>	EN ISO 24342 (EN 427)	36 @ 304.8 x 304.8mm = 3.34m <sup>2</sup> (12" x 12" = 35.95ft <sup>2</sup> ) 18 @ 304.8 x 609.6mm = 3.34m <sup>2</sup> (12" x 24" = 35.95ft <sup>2</sup> ) 36 @ 152.4 x 609.6mm = 3.34m <sup>2</sup> (6" x 24" = 35.95ft <sup>2</sup> )
	<b>Total Weight</b>	EN ISO 23997 (EN 430)	3600g/m <sup>2</sup> (6.64lb/sq.yd)
	<b>General Performance</b>	ISO 10582 (EN 649) ASTM F1700	Conforms Class III Type A&B
	<b>Use Area</b>	ISO 10874 (EN 685)	
	<b>Acoustic Impact Sound Reduction</b>	ASTM E90/492	55 STC
	<b>Impact Insulation Class</b>	ASTM E90/492	IIC 39
	<b>Resistance to Chemicals</b>	ASTM F925	Excellent - Chart available upon request
	<b>Reaction to Fire</b>	ASTM E648 EN 13501-1 ASTM E662 CAN/ULC S-102.2	Class 1 Class Bfl-S1 <450 PASS FSV <300; SDV <500
	<b>Abrasion Resistance</b>	EN 649 ISO 10582	Group T Type I
	<b>Flexibility</b>	ASTM F137	1" - PASS
	<b>Slip Resistance</b>	EN 13893 DIN 51130 AS 4586 ASTM D2047	Class DS (dry condition) R10 R10 >0.5
	For safety flooring with sustainable wet slip resistance, refer to Expona Control or the Polysafe ranges.		
	<b>Residual Indentation</b>	ISO 24343-1 (EN 433) ASTM F970 ASTM F1914	≤0.05mm (≤0.002") ≤0.005" @750 psi ≤0.005"
	<b>Dimensional Stability</b>	ISO 23999 (EN 434) ASTM F2199	≤0.1% max Pass
	<b>Thermal Conductivity</b>	EN 12524	0.25W/(m.K)
	<b>Underfloor Heating</b>		Suitable, max 27°C
	<b>Resistance to Light</b>	ASTM F1515	ΔE ≤ 8.0 - MEETS
	<b>Light Fastness</b>	ISO 105-B02	(Method 3) ≥6
	<b>Resistance to Heat</b>	ASTM F1514	ΔE ≤ 8.0 - MEETS
	<b>Castor Chair (continuous use)</b>	ISO 4918 (EN 425)	Suitable
	<b>Static Electrical Propensity</b>	EN 1815	≤2.0kV Classified as 'antistatic'
	<b>VOC Emissions</b>	Indoor Air Comfort GOLD AgBB/ABG VOC test FloorScore Finnish M1	Eurofins certified product Very low emissions Certified Certified
	<b>Responsible Sourcing</b>	BES 6001 SA 8000	Very Good Approved factory
<b>Environmentally Preferable Flooring</b> - Polyflor Camaro PUR achieves BRE Global A+ rating (ENP 429). Generic EN 15804 Environmental Product Declaration (EPD) available on request. It is 100% recyclable and contains average 40% recycled material. Recyclable via the Recofloor scheme. Visit <a href="http://www.polyflor.ca/sustainability">www.polyflor.ca/sustainability</a> .			
<b>PUR</b> - Polyflor Camaro PUR features a high quality, cross-linked polyurethane reinforcement, UV cured to provide a low-cost, polish free maintenance regime for the lifetime of the flooring.			
	For information regarding handling and installation, adhesives, maintenance, applications, chemical resistance and product warranty, consult Polyflor Customer Technical Services email <a href="mailto:tech@polyflor.ca">tech@polyflor.ca</a> . The data presented is correct at the time of printing. For latest information, please visit our website <a href="http://polyflor.ca">polyflor.ca</a> . Decoration and shade may vary slightly from the samples shown.		

